5

10

What is claimed is:

- 1. A polymer compound comprising:
- i) a polymerization unit represented by $-\left(CHR^3-CR^4\left(-L^1-Y^1\right)\right)_x-\left(CHR^5-CR^6\left(-L^2-Y^2\right)\right)_y-\text{; and}$
- ii) a silane coupling group represented by $-S-(CH_2)_n-Si-(R^1)_m\left(OR^2\right)_{3-m}\text{, as a terminal of the polymer,}$

wherein R^1 , R^2 , R^3 , R^4 , R^5 , and R^6 each independently represents a hydrogen atom or a hydrocarbon group having 1 to 8 carbon atoms; m represents 0, 1 or 2; n represents an integer of 1 to 8; x is 100 to 1 mol%; y is 0 to 99 mol%; x + y = 100 mol%; L^1 and L^2 each independently represents a single bond or an organic connecting group; and Y^1 and Y^2 each independently represents $-N(R^7)(R^8)$, -OH, $-NHCOR^7$, $-COR^7$, $-CO_2M$, or $-SO_3M$, wherein R^7 and R^8 each independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms and M represents a hydrogen atom, an alkali metal, an alkaline earth metal, or an onium.

- The polymer compound according to claim 1, which
 has a weight average molecular weight of 1,000 to 100,000.
 - 3. A lithographic printing plate base comprising: a support; and a hydrophilic layer containing solid particles to a surface of which a hydrophilic polymer is chemically bonded.

25

10

15

- 4. The lithographic printing plate base according to claim 3, which further comprises an undercoat layer between the support and the hydrophilic layer.
- 5. The lithographic printing plate base according to claim 3, wherein the hydrophilic polymer is a polymer compound according to claim 1.
 - 6. The lithographic printing plate base according to claim 3, wherein the support has a roughened surface.
 - 7. The lithographic printing plate base according to claim 3, wherein the solid particles are inorganic particles.
 - 8. The lithographic printing plate base according to claim 7, wherein the inorganic particles have an average particle size of 10 μm or less.
- 9. The lithographic printing plate base according to claim 3, wherein the hydrophilic polymer has a silane coupling group as a terminal thereof, and the silane coupling group is chemically bonded to the surface of the solid particles.
- 10. The lithographic printing plate base according 25 to claim 3, wherein the hydrophilic layer has a thickness of

0.001 to 10 g/m^2 .

11. The lithographic printing plate base according to claim 3, wherein the undercoat layer comprises a hydrophilic5 binder and silica.